



Color Copy coated glossy has a coating specially adapted to digital colour laser printing with a unique gloss effect. It is especially suitable for leaflets, annual reports and brochures.



**Technical Data:** COLOR COPY COATED GLOSSY

<b>Basis weight</b>	g/m <sup>2</sup>	ISO 536		<b>170 ± 4.0</b>
<b>Caliper</b>	µm	ISO 534		<b>136 ± 6</b>
<b>Smoothness Bekk</b>	sec	ISO 5627		<b>500 ± 150</b>
<b>Opacity</b>	%	ISO 2471	<b>min</b>	<b>96.0</b>
<b>Moisture abs.</b>	%	ISO 287		<b>4.8 ± .6</b>
<b>Brightness UV</b>	%	ISO 2470		<b>103.0 ± 2.0</b>
<b>CIE Whiteness</b>	%	ISO 11475		<b>139 ± 2.5</b>
<b>Gloss 75°</b>	TS %	TAPPI T 480		<b>75 ± 4</b>

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

This specification is valid for one year after issue.



Color Copy coated glossy has a coating specially adapted to digital colour laser printing with a unique gloss effect. It is especially suitable for leaflets, annual reports and brochures.



**Technical Data:** COLOR COPY COATED GLOSSY

<b>Basis weight</b>	g/m <sup>2</sup>	ISO 536		<b>135 ± 3.0</b>
<b>Caliper</b>	µm	ISO 534		<b>107 ± 4</b>
<b>Smoothness Bekk</b>	sec	ISO 5627		<b>1000 ± 300</b>
<b>Opacity</b>	%	ISO 2471	<b>min</b>	<b>94.0</b>
<b>Moisture abs.</b>	%	ISO 287		<b>4.8 ± .6</b>
<b>Brightness UV</b>	%	ISO 2470		<b>103.0 ± 2.0</b>
<b>CIE Whiteness</b>	%	ISO 11475		<b>139 ± 2.5</b>
<b>Gloss 75°</b>	TS %	TAPPI T 480		<b>75 ± 4</b>

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

This specification is valid for one year after issue.



Color Copy coated glossy has a coating specially adapted to digital colour laser printing with a unique gloss effect. It is especially suitable for leaflets, annual reports and brochures.



**Technical Data:** COLOR COPY COATED GLOSSY

<b>Basis weight</b>	g/m <sup>2</sup>	ISO 536		<b>250 ± 8.0</b>
<b>Caliper</b>	µm	ISO 534		<b>213 ± 9</b>
<b>Smoothness Bekk</b>	sec	ISO 5627		<b>250 ± 75</b>
<b>Opacity</b>	%	ISO 2471	<b>min</b>	<b>99.0</b>
<b>Moisture abs.</b>	%	ISO 287		<b>4.8 ± .6</b>
<b>Brightness UV</b>	%	ISO 2470		<b>103.0 ± 2.0</b>
<b>CIE Whiteness</b>	%	ISO 11475		<b>139 ± 2.5</b>
<b>Gloss 75°</b>	TS %	TAPPI T 480		<b>75 ± 4</b>

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

This specification is valid for one year after issue.



Color Copy coated glossy has a coating specially adapted to digital colour laser printing with a unique gloss effect. It is especially suitable for leaflets, annual reports and brochures.



**Technical Data:** COLOR COPY COATED GLOSSY

<b>Basis weight</b>	g/m <sup>2</sup>	ISO 536		<b>200 ± 6.0</b>
<b>Caliper</b>	µm	ISO 534		<b>162 ± 7</b>
<b>Smoothness Bekk</b>	sec	ISO 5627		<b>400 ± 120</b>
<b>Opacity</b>	%	ISO 2471	<b>min</b>	<b>98.0</b>
<b>Moisture abs.</b>	%	ISO 287		<b>4.8 ± .6</b>
<b>Brightness UV</b>	%	ISO 2470		<b>103.0 ± 2.0</b>
<b>CIE Whiteness</b>	%	ISO 11475		<b>139 ± 2.5</b>
<b>Gloss 75°</b>	TS %	TAPPI T 480		<b>75 ± 4</b>

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA

This specification is valid for one year after issue.