

CreatorSilk Art

EN

Coated Paper 2 Sides Gloss

Property		Unit	Tolerance										
Substance	ISO 536	TAPPI T410	gsm	± 4%	115	135	150	170	200	250	300	350	400
Thickness	ISO 534	TAPPI T411	µm	± 4%	87	103	109	125	149	191	234	288	330
Brightness R457 D65	ISO 2470-2	-	%	± 2	95	95	95	95	95	95	95	95	95
Whiteness CIE D65/10°	ISO 11475	-	-	± 3	120	120	120	120	120	120	120	120	120
Opacity	ISO 2471	TAPPI T519	%	-2.0	93	95,5	96	97	-	-	-	-	-
Smoothness Bekk	ISO 5627	TAPPI T479	s	±30%	1000	1000	1000	850	600	500	350	350	200
Relative Humidity	-	TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50

- Last updated: **15-02-16**
- Values are subject to change without notice.

ES

Estucado 2 Caras Brillante

Propiedad		Unidades	Tolerancia										
Gramaje	ISO 536	TAPPI T410	gsm	± 4%	115	135	150	170	200	250	300	350	400
Calibre	ISO 534	TAPPI T411	µm	± 4%	87	103	109	125	149	191	234	288	330
Brightness R457 D65	ISO 2470-2	-	%	± 2	95	95	95	95	95	95	95	95	95
Blancura CIE D65/10°	ISO 11475	-	-	± 3	120	120	120	120	120	120	120	120	120
Opacidad	ISO 2471	TAPPI T519	%	-2.0	93	95,5	96	97	-	-	-	-	-
Lisura Bekk	ISO 5627	TAPPI T479	s	±30%	1000	1000	1000	850	600	500	350	350	200
Humedad relativa	-	TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50

- Última actualización: **15-02-16**
- Los valores están sujetos a cambio sin aviso previo.

FR

Couché 2 Faces Brillant

Propriété		Unité	Tolérance										
Grammage	ISO 536	TAPPI T410	gsm	± 4%	115	135	150	170	200	250	300	350	400
Épaisseur	ISO 534	TAPPI T411	µm	± 4%	87	103	109	125	149	191	234	288	330
Blancheur R457 D65	ISO 2470-2	-	%	± 2	95	95	95	95	95	95	95	95	95
Blancheur CIE D65/10°	ISO 11475	-	-	± 3	120	120	120	120	120	120	120	120	120
Opacité	ISO 2471	TAPPI T519	%	-2.0	93	95,5	96	97	-	-	-	-	-
Lissé Bekk	ISO 5627	TAPPI T479	s	±30%	1000	1000	1000	850	600	500	350	350	200
Humidité relative	-	TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50

- Dernière actualisation : **15-02-16**
- Ces valeurs peuvent être modifiées sans avis préalable.

IT

Carta Patinata Lucida

Proprietà		Unità	Tolleranza										
Grammatura	ISO 536	TAPPI T410	gsm	± 4%	115	135	150	170	200	250	300	350	400
Spessore	ISO 534	TAPPI T411	µm	± 4%	87	103	109	125	149	191	234	288	330
Bianco R457 D65	ISO 2470-2	-	%	± 2	95	95	95	95	95	95	95	95	95
Bianco CIE D65/10°	ISO 11475	-	-	± 3	120	120	120	120	120	120	120	120	120
Opacità	ISO 2471	TAPPI T519	%	-2.0	93	95,5	96	97	-	-	-	-	-
Liscio Bekk	ISO 5627	TAPPI T479	s	±30%	1000	1000	1000	850	600	500	350	350	200
Umidità relativa	-	TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50

- Ultima revisione: **15-02-16**
- I valori sono soggetti a modifiche senza preavviso.

PT

Couché 2 Faces Brilhante

Propriedade		Unidade	Tolerância										
Gramagem	ISO 536	TAPPI T410	gsm	± 4%	115	135	150	170	200	250	300	350	400
Calibre	ISO 534	TAPPI T411	µm	± 4%	87	103	109	125	149	191	234	288	330
Brancura R457 D65	ISO 2470-2	-	%	± 2	95	95	95	95	95	95	95	95	95
Brancura CIE	ISO 11475	-	-	± 3	120	120	120	120	120	120	120	120	120
Opacidade	ISO 2471	TAPPI T519	%	-2.0	93	95,5	96	97	-	-	-	-	-
Lisura Bekk	ISO 5627	TAPPI T479	s	±30%	1000	1000	1000	850	600	500	350	350	200
Humidade relativa	-	TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50

- Última actualização: **15-02-16**
- Os valores estão sujeitos a mudanças sem pré-aviso.

