

# CreatorVol

EN

## 2 Side Coated Bulky Matt

Property			Units	Tolerance	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380
Substance	ISO 536	TAPPI T410	gsm	± 4%	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380
Thickness	ISO 534	TAPPI T411	µm	± 4%	93	104	117	123	140	147	156	182	210	236	265	297	327	392	394
Brightness R457 D65	ISO 2470-2	-	%	± 2	96	96	96	96	96	96	96	96	96	96	96	96	96	96	96
Whiteness CIE D65 / 10'	ISO 11475	-	-	± 3	121	121	121	121	121	121	121	121	121	121	121	121	121	121	121
Opacity	ISO 2471	TAPPI T519	%	-2	92,0	93,5	94,5	95,0	96,0	96,5	97,5	98,0	-	-	-	-	-	-	-
Roughness Bendsen	ISO 8791-2	TAPPI UM-535	ml/min	≤1,2*STD	100	100	100	100	-	-	-	-	-	-	-	-	-	-	-
Smoothness Bekk	ISO 5627	TAPPI T479	s	≥0,7*STD	-	-	-	-	100	100	100	100	100	100	100	100	90	80	90
Relative Humidity	-	TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Last updated: **30-10-14**
- Values are subject to change without notice.

ES

## Estucado 2 Caras Mate Volumen

Propiedad			Unidades	Tolerancia	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380
Gramaje	ISO 536	TAPPI T410	gsm	± 4%	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380
Calibre	ISO 534	TAPPI T411	µm	± 4%	93	104	117	123	140	147	156	182	210	236	265	297	327	392	394
Blancura R457 D65	ISO 2470-2	-	%	± 2	96	96	96	96	96	96	96	96	96	96	96	96	96	96	96
Blancura CIE D65 / 10'	ISO 11475	-	-	± 3	121	121	121	121	121	121	121	121	121	121	121	121	121	121	121
Opacidad	ISO 2471	TAPPI T519	%	-2	92,0	93,5	94,5	95,0	96,0	96,5	97,5	98,0	-	-	-	-	-	-	-
Rugosidad Bendsen	ISO 8791-2	TAPPI UM-535	ml/min	≤1,2*STD	100	100	100	100	-	-	-	-	-	-	-	-	-	-	-
Lisura Bekk	ISO 5627	TAPPI T479	s	≥0,7*STD	-	-	-	-	100	100	100	100	100	100	100	100	90	80	90
Humedad relativa	-	TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Última actualización: **30-10-14**
- Los valores están sujetos a cambio sin aviso previo.

FR

## Couché 2 Faces Mat à Main

Caractéristique			Unités	Tolérance	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380
Grammage	ISO 536	TAPPI T410	gsm	± 4%	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380
Épaisseur	ISO 534	TAPPI T411	µm	± 4%	93	104	117	123	140	147	156	182	210	236	265	297	327	392	394
Blancheur R457 D65	ISO 2470-2	-	%	± 2	96	96	96	96	96	96	96	96	96	96	96	96	96	96	96
Blancheur CIE D65 / 10'	ISO 11475	-	-	± 3	121	121	121	121	121	121	121	121	121	121	121	121	121	121	121
Opacité	ISO 2471	TAPPI T519	%	-2	92,0	93,5	94,5	95,0	96,0	96,5	97,5	98,0	-	-	-	-	-	-	-
Rugosité Bendsen	ISO 8791-2	TAPPI UM-535	ml/min	≤1,2*STD	100	100	100	100	-	-	-	-	-	-	-	-	-	-	-
Lissé Bekk	ISO 5627	TAPPI T479	s	≥0,7*STD	-	-	-	-	100	100	100	100	100	100	100	100	90	80	90
Humidité relative	-	TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Dernière actualisation: **30-10-14**
- Ces valeurs sont sujettes à modification sans avis préalable

PT

## Couché 2 Faces Mate Volume

Propriedade			Unidade	Tolerância	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380
Gramagem	ISO 536	TAPPI T410	gsm	± 4%	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380
Calibre	ISO 534	TAPPI T411	µm	± 4%	93	104	117	123	140	147	156	182	210	236	265	297	327	392	394
Brancura R457 D65	ISO 2470-2	-	%	± 2	96	96	96	96	96	96	96	96	96	96	96	96	96	96	96
Brancura CIE D65 / 10'	ISO 11475	-	-	± 3	121	121	121	121	121	121	121	121	121	121	121	121	121	121	121
Opacidade	ISO 2471	TAPPI T519	%	-2	92,0	93,5	94,5	95,0	96,0	96,5	97,5	98,0	-	-	-	-	-	-	-
Aspereza Bendsen	ISO 8791-2	TAPPI UM-535	ml/min	≤1,2*STD	100	100	100	100	-	-	-	-	-	-	-	-	-	-	-
Lisura Bekk	ISO 5627	TAPPI T479	s	≥0,7*STD	-	-	-	-	100	100	100	100	100	100	100	100	90	80	90
Humidade relativa	-	TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Última actualização: **30-10-14**
- Os valores estão sujeitos a mudanças sem pré-aviso.

