

TECHNICAL SPECIFICATION

JULY 2019

SUBSTANCE	CALIPER	BULK	STIFFNESS			
			TABER 15°		L&W 5° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m²	µm	cm³/g	mN.m	mN.m	mN.m	mN.m
250	338	1.35	8.0	3.6	15.5	6.8
275	375	1.36	10.8	4.8	20.8	9.1
300	407	1.36	13.5	6.0	27.0	11.8
325	445	1.37	17.0	7.5	33.0	14.5
350	485	1.38	20.0	8.8	40.0	17.5
375	530	1.41	24.6	10.8	49.0	21.4
400	555	1.39	29.6	13.0	59.2	25.8
425	585	1.38	35.1	15.4	68.6	29.9
450	620	1.37	41.6	18.2	80.3	35.1
475	670	1.41	47.0	20.5	91.6	39.9

(*) THE L&W 5° STIFFNESS IS ORIENTATIVE/CALCULATED.

BRIGHTNESS		
TOP	79,5 +/- 1,5%	ISO 2470-2

TOLERANCES (1)		
SUBSTANCE	+/- 4%	
CALIPER	+/- 5%	
STIFFNESS	- 15%	
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

(1) TOLERANCES BASED UPON 95% OF THE MEASURED VALUES.